MASTERFLEX
WATERPROOFING SYSTEM

TECHNICAL DATA SHEET
FICHA TÉCNICA

# PRODUCT NAME:
# MASTERFLEX®
# PATCHING WEAVE




**PRODUCT DESCRIPTION:**
MASTERFLEX® PATCHING WEAVE is a strong and flexible white patching weave made of the finest fiber-glass materials. This product is designed to be used with MASTERFLEX® CRACK FILLER to repair and waterproof cracks, holes, seems and joints before roof coating applications. Its durable open mesh weave guarantees excellent bonding and allows for expansion and contraction.

**PRODUCT USE:**
Recommended to be used with MASTERFLEX® CRACK FILLER to repair and waterproof cracks, holes, seems and joints before the roof coating applications over a variety of substrates including: concrete, metal, wood, asphalt and polyurethane foam.

**PRODUCT FEATURES:**

- Strong fiber-glass patching weave
- Compatible with elastomeric and silicone coatings
- Allows for normal contraction and expansion of cracks
- Suitable for exterior applications. Will not rot or decay

**PRODUCT SPECIFICATIONS:**
**Product Identification:**
VA0600 MASTERFLEX® PATCHING WEAVE

**Width of Roll:** 5.5” (13.97 cm)

**Length of Roll:** 50’ (15.24 m)

**Average Net Weight (oz.yd²):** 2.15 lb (0.98 kg)

**Average Tensile Strength per 1” (2.5 cm) width:**

- Warp Threads: 85 min
- Filling Threads: 85 min

**Thickness:** .005

**SURFACE PREPARATION:**
Clean the surface thoroughly by removing all dust, dirt, grease, mold, mildew, loose roof coating, and any other contaminants. Allow the surface to dry completely for at least 24 hours.

**APPLICATION:**
Apply an initial coat of MASTERFLEX® CRACK FILLER using a putty knife or brush over the area to be repaired. Extend the application approximately 2-3 inches beyond each side of the crack, seam, joint, or repair area. While the coating is still wet, embed MASTERFLEX® PATCHING WEAVE into the fresh material, applying firm pressure to ensure complete saturation and proper adhesion. Apply a second coat of MASTERFLEX® CRACK FILLER over the entire repair area, fully encapsulating the reinforcement fabric. The MASTERFLEX® PATCHING WEAVE should not be visible after the second coat has been applied. Allow the repair to dry for 24 hours before proceeding with subsequent coating applications.

**CLEAN UP:**
Wash patching compound tools in warm soapy water immediately after use.

**SAFETY INFORMATION:**
Avoid eye and skin contact. Loose fibers can cause irritation. Cloth or leather gloves are recommended when handling. Store in dry place.

**WARRANTY:** The warranty of this product is limited only to the replacement of the product if it should fail to comply with quality standards or specifications. Master Paints & Chemical Corp. does not guarantee and shall not be liable for damages arising out of purchaser’s failure to apply the product in accordance with our instructions. This warranty excludes labor and costs of labor for the application or removal of any product, and any incidental or consequential damages. If not satisfied as warranted, contact Master Paints & Chemical Corp. with sales receipt(s).



MASTER PAINTS & CHEMICAL CORP.
PO Box 560248 Guayanilla PR 00656-0248
(787) 740-5254 • Tel. (787) 835-4000
Carr. 127 Km 12.7 Bo Magas Guayanilla PR
www.masterflexpr.com

HECHO CON 100% ENERGIA SOLAR
Hecho en Puerto Rico